University of Massachusetts Amherst

From the Selected Works of George W. Huber

2012

Catalytic fast pyrolysis of wood and alcohol mixtures in a fluidized bed reactor

George W Huber, *University of Massachusetts - Amherst*

H. Zhang

T. R Carlson

R. Xiao

Available at: https://works.bepress.com/george_huber/9/

Green Chemistry

Cutting-edge research for a greener sustainable future

www.rsc.org/greenchem

Volume 14 | Number 1 | January 2012 | Pages 1–234

ISSN 1463-9262

RSC Publishing

COVER ARTICLE

Huber *et al.*

Catalytic fast pyrolysis of wood and alcohol mixtures
in a fluidized bed reactor

Catalytic fast pyrolysis of wood and alcohol mixtures in a fluidized bed reactor

Huiyan Zhang,^{a,b} Torren R. Carlson,^b Rui Xiao^a and George W. Huber^{*b}

Received 27th May 2011, Accepted 19th August 2011

DOI: 10.1039/c1gc15619e

Catalytic fast pyrolysis (CFP) of pine wood, alcohols (methanol, 1-propanol, 1-butanol and 2-butanol) and their mixtures with ZSM-5 catalyst were conducted in a bubbling fluidized bed reactor. The effects of temperature and weight hourly space velocity (WHSV) on the product carbon yields and selectivities of CFP of pure pine wood and methanol were investigated. A maximum carbon yield of petrochemicals (aromatics + C₂–C₄ olefins + C₅ compounds) from pine wood of 23.7% was obtained at a temperature of 600 °C and WHSV of 0.35 h⁻¹. A maximum petrochemical yield from methanol of 80.7% was obtained at a temperature of 400 °C and WHSV of 0.35 h⁻¹. Thus, the optimal conditions for conversion of pine wood and methanol are different. The CFP of pine wood and methanol mixtures was conducted at 450 °C and 500 °C. The hydrogen to carbon effective (H/C_{eff}) ratio of the feed was adjusted by changing the relative amount of methanol and wood. The petrochemical yield was a function of the H/C_{eff} ratio and more petrochemicals are produced from biomass when methanol is added to the CFP process. Co-feeding of ¹²C pine wood and ¹³C methanol was carried out at 450 °C. The isotopic study showed that all the hydrocarbon products contained mixtures of ¹²C and ¹³C, indicating that the carbon is mixed within the zeolite. However, the distribution of carbon was skewed depending on the product. The toluene, xylene, propylene and butenes contained more ¹³C. The naphthalene and ethylene contain more ¹²C. Wood was also co-processed with 1-propanol, 1-butanol, and 2-butanol, which showed a similar effect as methanol with an increasing petrochemical yield with an increasing H/C_{eff} ratio of the feed. This paper demonstrates that CFP can selectively produce a mixture of compounds where the overall yield is a function of the H/C_{eff} ratio of the feed.

1. Introduction

Environmental issues caused by using fossil fuels, the growing energy demand and the depletion of petroleum resources have stimulated the development of new sources for the production of renewable liquid fuels.^{1,2} Due to its low cost and abundant availability, lignocellulosic biomass has been studied world wide to produce liquid fuels and chemicals.^{3–59} There are several routes for converting solid biomass or its derivatives to liquid fuels and chemicals, such as aqueous-phase reformation,^{18–24} pyrolysis followed by vapors upgrading,^{25–29} gasification followed by Fischer–Tropsch synthesis to produce liquid alkanes,^{30–32} hydrodeoxygenation of pyrolysis oil,^{33–35} and the conversion of pyrolysis oil or its derivatives to aromatic hydrocarbons over zeolite catalysts.^{36–46} All of these routes involve multiple steps and

thus greatly increase the cost of biomass processing. Catalytic fast pyrolysis (CFP) is a new promising technology to directly convert solid biomass into hydrocarbon products that fit directly into the current infrastructure.^{47–55} CFP is a single step process that uses inexpensive zeolite catalysts. Furthermore, the reactor is operated at atmospheric pressure and does not require the use of hydrogen. One of the critical factors that will influence the future prospects of biofuels is product flexibility.⁵⁶ CFP of biomass can produce five of the six primary petrochemicals, including benzene, toluene, xylene, ethylene and propylene.⁴⁸ One of the critical challenges with CFP is to increase the yield of usable petrochemicals.

A parameter called the hydrogen to carbon effective (H/C_{eff}) ratio (also called the effective hydrogen index) can be used to compare the relative amount of hydrogen present in different feeds.⁵⁷ The H/C_{eff} ratio is defined in eqn (1), where H, C and O are the mol of hydrogen, carbon and oxygen, respectively.

$$H/C_{\text{eff}} = \frac{H - 2O}{C} \quad (1)$$

^aSchool of Energy and Environment, Southeast University, Nanjing, 210096, PR China

^bDepartment of Chemical Engineering, University of Massachusetts-Amherst, Amherst, MA 01002, USA.
E-mail: huber@ecs.umass.edu; Tel: +4135450276

Fig. 1 Overall reaction chemistry for the co-catalytic fast pyrolysis of cellulose and methanol. Adapted from Carlson *et al.*⁴⁸

Chen *et al.*⁵⁷ showed that feedstocks with an H/C_{eff} ratio less than 1 are difficult to upgrade to premium products over a ZSM-5 catalyst due to rapid deactivation of the catalyst. The H/C_{eff} ratio of petroleum-derived feeds ranges from 1 (for benzene) to slightly over 2 (for liquid alkanes), whereas that of biomass is only from 0 to 0.3. Thus, biomass is a hydrogen-deficient molecule. We have recently shown that the yield of usable petrochemical products from zeolite conversion of different biomass-derived feedstocks is a function of the H/C_{eff} ratio of the feedstock.^{58,59} This suggests that the petrochemical yield from CFP of biomass could be increased by co-feeding in an additional feedstock that has a high H/C_{eff} ratio. Methanol has an H/C_{eff} ratio of 2 and has been shown to give high yields of hydrocarbon products when processed over a zeolite catalyst.^{60–62} Therefore, methanol could potentially be co-fed with biomass to increase the overall H/C_{eff} ratio of the feed. Methanol is a liquid at room temperature and easier to transport than hydrogen, which is a gas at room temperature.

The reaction pathways for co-catalytic fast pyrolysis (co-CFP) of cellulose (a biomass model compound) and methanol are shown in Fig. 1. The CFP of cellulose involves both homogeneous and heterogeneous reactions. The first step is the homogeneous thermal decomposition of cellulose to a liquid intermediate that is then converted into anhydrosugars.^{63–65} The anhydrosugars are relatively thermally stable and do not form large amounts of coke in the gas phase.⁶⁶ However, the anhydrosugars can undergo dehydration and re-arrangement reactions to form intermediate oxygenates, such as furans and smaller aldehydes. These reactions can happen in either the gas phase or in the presence of a catalyst.⁶⁷ In the second step, these intermediate oxygenates then diffuse into the zeolite catalyst pores and form monocyclic aromatics, C_2 – C_4 olefins and C_5 compounds through a series of dehydration, decarbonylation, decarboxylation and oligomerization reactions. The aromatic formation rate is relatively slow compared to the pyrolysis reactions.⁶⁷ The major competing reaction with the formation of aromatics is the formation of coke from the

polymerization of the furans and oxygenated pyrolysis vapors. The aromatic formation reaction proceeds through a common intermediate or “hydrocarbon pool” within the zeolite framework.^{68–75} Co-feeding methanol with biomass may alter the “hydrocarbon pool” and increase the rate of aromatic production.

We know of three papers in the literature that have previously reported on co-feeding of biomass or its derivatives with methanol over HZSM-5 catalysts.^{40,76,77} These studies all reported increased aromatic and olefin yields when methanol is co-fed with the biomass or its derivatives. Gayubo *et al.*^{40,76} conducted co-feeding of bio-oil and methanol in a fluidized bed and conical spouted bed reactor with HZSM-5 and Ni/HZSM-5 catalysts. They reported that co-feeding of methanol with the pyrolysis oil increased the C_2 – C_4 olefin yield and decreased the CO , CO_2 , and coke yields. Evans and Milne⁷⁷ co-fed methanol with wood in a quartz microreactor with HZSM-5 catalyst. They showed that more aromatic products were formed with the co-feeding process.

The objective of this work is to study the CFP of pine wood and methanol mixtures in a fluidized bed reactor to see if the overall petrochemical yield can be improved by the addition of alcohol feeds. The effect of temperature and weight hourly space velocity (WHSV) on the product carbon yields and selectivities of CFP of pine wood and methanol are studied to determine a suitable operation condition for co-CFP of these feed mixtures. We compare the economic potential of CFP of pine wood and methanol mixtures to assess the potential benefits of co-feeding. Isotopically labelled ^{13}C methanol was processed with pine wood to identify how methanol and wood are incorporated into the final products. We also study the co-CFP of pine wood with other alcohols, such as 1-propanol, 1-butanol and 2-butanol to determine if these feeds can be used to enhance the petrochemical yield. This paper thus provides critical insights as to how the yield of petrochemicals can be increased by co-feeding of pine wood with feeds that have a high H/C_{eff} ratio like alcohols.

2. Experimental section

2.1 Materials

2.1.1 Feeds. ^{13}C methanol, 1-propanol, 1-butanol and 2-butanol were purchased from Sigma-Aldrich and used as feedstocks without any pretreatment. ^{13}C methanol (Product ID: CLM-359-5) with 99 atom% ^{13}C was bought from Cambridge Isotope Laboratories, Inc. The wood used in this study is eastern pine wood sawdust sourced from a local sawmill. Prior to the experiments, the wood was ground with a high-speed rotary cutting mill and then sieved to yield a particle size of 18–120 mesh (120–880 micron). The elemental composition of the wood is 46.2 wt% carbon, 6.0 wt% hydrogen and 47.3 wt% oxygen (by difference). The proximate analysis result is 4.0 wt% moisture, 74.2 wt% volatile, 21.3 wt% fixed carbon and 0.5 wt% ash. On the dry basis the approximate molecular formula of the wood is therefore $\text{C}_{3.8}\text{H}_{5.8}\text{O}_{2.7}$.

2.1.2 Catalyst. The catalyst used in this work is a commercial spray dried 40% ZSM-5 catalyst (Intercat, Inc.). The particle size of the catalyst is from 150 to 230 mesh (62–106 micron). For a typical run, 30 g catalyst is loaded in the reactor. Prior to reactions, the catalyst was calcined in the fluidized bed reactor for 5 h at 600 °C in 800 mL min⁻¹ flowing air.

2.2 Experimental setup

CFP and co-CFP of pine wood and alcohols were conducted in a fluidized bed reactor system, as shown in Fig. 2, which can be found elsewhere.⁴⁸ The fluidized bed reactor is a 2 inch ID 316 stainless steel tube with a freeboard height of 10 inch. The catalyst bed is supported by a distributor plate made from stacked 316 stainless steel mesh (300 mesh). The pine wood is fed into the side of the reactor (1 inch above the distributor plate) by a stainless steel auger from a sealed feed hopper. The hopper is swept with helium at a rate of 200 mL min⁻¹ to maintain an inert environment in the feeding unit. Methanol is fed into the fluidizing gas stream at the inlet of the plenum by a syringe pump. The methanol vaporizes in the gas stream and enters the reactor through the distributor plate as vapours. Ultra high purity helium (99.99%) was used as the fluidizing gas. The gas flow rate was set as 1200 mL min⁻¹ and controlled by a mass flow controller. Both the reactor and the inlet gas stream are heated to reaction temperature before reaction. A cyclone is located at the exit of the reactor to remove and collect entrained

Fig. 2 The schematic of the fluidized bed reactor system for catalytic fast pyrolysis of biomass and alcohols.

solid particles. Following the cyclone, the vapours flow into a condenser train. The first three condensers are operated at 0 °C in an ice bath and the following four condensers are operated at -55 °C in a dry ice/acetone bath. The non-condensable vapours exiting the condenser train are collected by a gas sampling bag and analyzed by GC/FID and GC/TCD. A carrier gas flow rate of 1400 mL min⁻¹ was used for all experiments, as measured by a bubble flow meter. We used GC/FID to analyze the amount of gas products produced. Ethanol was added to the condensers to help condense the condensable products. All liquid products were soluble in the ethanol. These liquid products were then analyzed by GC-FID. For the isotopically labelled feed run, the gas samples and liquids were further analyzed by GC/MS. For a typical run, pine wood is fed to the reactor for 30 min. At the end of the run, the reactor is purged with 1200 mL min⁻¹ for another 30 min to strip any remaining product from the catalyst. After reaction, the catalyst is regenerated at 600 °C in 800 mL min⁻¹ flowing air. The effluent gas during regeneration mainly contains CO₂, CO and H₂O, which was passed in series through a copper catalyst, a dryrite trap and an ascarite trap. The copper catalyst is a copper oxide powder (13% CuO on alumina, Sigma-Aldrich) and is operated at 250 °C to convert CO to CO₂. The coke carbon yield is determined by the mass of CO₂ captured by the ascarite trap.

3. Results

3.1 Catalytic fast pyrolysis of pine wood

3.1.1 Effect of reaction temperature on pyrolysis product yields and selectivities. Fig. 3 and Table 1 show the product carbon yields for CFP of pine wood in the fluidized bed reactor at different temperatures. As can be seen from the figure, the aromatic and olefin yields go through a maximum of 13.9% and 9.4% at 600 °C, respectively. The maximum total carbon yield of petrochemicals (aromatics + C₂–C₄ olefins + C₅ compounds) is 23.7%, which occurs at 600 °C. The coke and unidentified oxygenates yields decrease with increasing temperature from 40.4% and 28.4% at 400 °C to 19.7% and 2.9% at 650 °C, respectively. The CO and methane yields increase with increasing temperature from 16.2% and 0.3% at 400 °C to 44.1% and 6.9% at 650 °C, respectively. The detailed product carbon yields and selectivities are listed in Table 1. The main aromatic products include benzene, toluene, xylene and naphthalene. Benzene and naphthalene selectivities increase, while xylene and

Fig. 3 Product yields as a function of temperature for CFP of pine wood. Reaction conditions: ZSM-5 catalyst, 0.35 h⁻¹ WHSV, 1200 mL min⁻¹ helium fluidizing flow rate, 30 min reaction time. Key: (a) ■ Aromatics, ▲ C₂–C₄ olefins, ● C₅ compounds, ◆ Unidentified; (b) □ Methane, △ CO₂, ○ CO, ◇ Coke.

Table 1 Detailed product yields and selectivities for CFP of pine wood at various temperatures and WHSV = 0.35 h⁻¹. Aromatic selectivity is defined as the moles of carbon in the product divided by the total moles aromatic carbon. Olefin selectivity is defined as the moles of carbon in the product divided by the total moles olefin carbon

Compound	T/°C				
	400	450	500	600	650
<i>Overall yields</i>					
Aromatics	4.6	5.9	10.5	13.9	7.8
C ₂ –C ₄ olefins	2.7	4.3	5.4	9.4	6.8
C ₅ compounds	0.3	0.5	0.3	0.5	0.3
Petrochemicals	7.6	10.7	16.2	23.7	14.9
Methane	0.3	0.6	2.1	4.3	6.9
CO ₂	7.1	8.9	7.7	9.5	11.6
CO	16.2	19.7	25.6	32.2	44.1
Coke	40.4	41.6	31.7	26.7	19.7
Total balance	71.7	81.4	83.3	96.4	97.1
Unidentified	28.4	18.6	16.7	3.6	2.9
<i>Aromatic selectivity</i>					
Benzene	13.4	10.8	15.3	20.8	38.8
Toluene	30.9	32.2	34.7	37.1	30.7
Ethyl-benzene	4.9	3.4	4.5	2.3	0
<i>p</i> -Xylene and <i>m</i> -Xylene	29.6	33.2	24.1	16.6	8.9
<i>o</i> -Xylene	7.1	4.8	3.5	3.2	2.2
Styrene	0	0	3.7	2.8	0
Benzofuran	3.0	4.3	1.6	1.9	0
Indene	2.4	2.6	3.3	2.6	1.8
Phenol	1.4	1.1	1.5	1.4	1.3
Naphthalene	7.3	7.7	7.7	11.2	16.4
<i>Olefin selectivity</i>					
Ethylene	36.5	54.9	49.0	52.8	66.4
Propylene	48.1	36.0	37.8	36.0	26.4
Butenes	7.2	7.2	7.0	6.0	3.8
Butadiene	8.2	1.9	6.2	5.2	3.4

ethyl benzene selectivities decrease with increasing temperature. The main C₂–C₄ olefins produced in the reactions include ethylene, propylene, butenes and butadiene. Propylene and butenes selectivities decrease and ethylene selectivity increases with increasing temperature.

3.1.2 Effect of weight hourly space velocity on pyrolysis product yields and selectivities. The product carbon yields for CFP of pine wood at 600 °C as a function of weight hourly space velocity (WHSV) are shown in Fig. 4 and Table 2. WHSV is defined as the mass flow rate of feed divided by the mass of catalyst in the reactor. A WHSV of 0.11–1.98 h⁻¹ was used for these experiments, which corresponds to feeding between 1.65–29.7 g of wood to the reactor. The aromatic and olefin yields go through a maximum at WHSV = 0.35 h⁻¹. The unidentified oxygenates yield increases from 2.6% at WHSV = 0.11 h⁻¹ to 17.3% at WHSV = 1.98 h⁻¹ with increasing WHSV. The methane yield increases from 3.0% to 6.5% with increasing WHSV. The CO yield goes through a maximum of 36.3% at WHSV = 0.60 h⁻¹. The CO₂ and coke yields decrease with increasing WHSV. The xylene and toluene selectivities decrease, whereas the benzene and naphthalene selectivities increase with increasing WHSV. The ethylene and butenes selectivities decrease with the increase of WHSV.

3.2 Catalytic conversion of methanol

3.2.1 Effect of reaction temperature on product yields and selectivities. Product carbon yields of catalytic conversion of

Table 2 Detailed product yields and selectivities for CFP of pine wood at various WHSV values and 600 °C. Aromatic selectivity is defined as the moles of carbon in the product divided by the total moles aromatic carbon. Olefin selectivity is defined as the moles of carbon in the product divided by the total moles olefin carbon

Compound	WHSV (h ⁻¹)					
	0.11	0.18	0.35	0.60	0.97	1.98
<i>Overall yields</i>						
Aromatics	6.7	10.4	13.9	11.4	9.8	4.4
C ₂ –C ₄ olefins	7.6	8.6	9.4	7.8	7.0	7.7
C ₅ compounds	0.7	0.8	0.5	0.3	0.4	0.1
Petrochemicals	15.0	19.8	23.7	19.5	17.2	12.3
Methane	3.0	2.9	4.3	5.9	5.3	6.5
CO ₂	18.2	14.3	9.5	8.2	7.7	8.4
CO	28.3	29.2	32.2	36.3	32.0	30.8
Coke	32.9	30.6	26.7	23.6	23.5	24.8
Total balance	97.4	96.8	96.4	93.4	85.7	82.7
Unidentified	2.6	3.2	3.6	6.6	14.3	17.3
<i>Aromatic selectivity</i>						
Benzene	25.4	21.7	20.8	24.3	29.2	36.4
Toluene	40.1	37.2	37.1	32.0	24.8	20.9
Ethyl-benzene	1.7	1.8	2.3	2.0	2.6	2.0
<i>p</i> -Xylene and <i>m</i> -Xylene	18.1	19.0	16.6	14.2	13.5	9.0
<i>o</i> -Xylene	3.8	1.1	3.2	4.2	2.8	2.8
Styrene	0	3.8	2.8	2.0	2.7	1.6
Benzofuran	0.3	1.6	1.9	2.2	2.8	2.9
Indene	1.4	2.3	2.6	3.5	2.6	2.3
Phenol	0.6	1.0	1.4	1.7	1.4	1.0
Naphthalene	8.7	10.6	11.2	13.9	17.7	21.3
<i>Olefin selectivity</i>						
Ethylene	55.6	49.3	52.8	61.1	53.3	49.4
Propylene	24.9	32.3	36.0	29.5	37.0	40.1
Butenes	14.2	12.3	6.0	4.6	4.8	5.9
Butadiene	5.2	6.0	5.2	4.9	4.9	4.6

Fig. 4 Product yields as a function of WHSV for CFP of pine wood. Reaction conditions: ZSM-5 catalyst, 600 °C. 1200 mL min⁻¹ helium fluidizing flow rate, 30 min reaction time. Key: (a) ■ Aromatics, ▲ C₂–C₄ olefins, ● C₅ compounds, ◆ Unidentified; (b) □ Methane, △ CO₂, ○ CO, ◇ Coke.

methanol at different temperatures with WHSV of 0.35 h⁻¹ are shown in Fig. 5 and Table 3. Temperature has a pronounced effect on the product distribution. The yields of C₂–C₄ olefins, aromatics, C₅ compounds and unidentified oxygenates decrease with increasing temperature. The yields of methane, CO₂, CO and coke increase with increasing temperature. Temperature has the biggest effect on the olefin and CO yields. The olefin yield decreases from 52.3% at 400 °C to 0.2% at 600 °C. The CO yield increases from 1.3% at 400 °C to 59.7% at 600 °C. The petrochemical yield decreases from 80.7% at 400 °C to 3.8% at 600 °C. Table 3 lists the detailed product yields and selectivities. The benzene and toluene selectivities increase and xylene selectivity decreases with the increase of temperature. At

Table 3 Detailed product yields and selectivities for catalytic conversion of methanol at various temperatures and WHSV = 0.35 h⁻¹. Aromatic selectivity is defined as the moles of carbon in the product divided by the total moles aromatic carbon. Olefin selectivity is defined as the moles of carbon in the product divided by the total moles olefin carbon

Compound	T/°C			
	400	450	500	600
<i>Overall yields</i>				
Aromatics	14.8	11.1	5.5	3.5
C ₂ –C ₄ olefins	52.3	52.6	34.6	0.2
C ₅ compounds	13.6	7.9	1.8	0.1
Petrochemicals	80.7	71.5	41.9	3.8
Methane	1.8	4.5	11.0	8.4
CO ₂	3.7	8.9	21.5	21.1
CO	1.3	5.1	21.0	59.7
Coke	1.8	2.1	2.9	5.5
Total balance	89.3	92.1	98.3	98.4
Unidentified	10.7	7.9	1.7	1.6
<i>Aromatic selectivity</i>				
Benzene	1.8	3.3	9.6	23.7
Toluene	11.1	15.6	19.3	40.6
Ethyl-benzene	1.8	1.6	2.5	2.0
<i>p</i> -Xylene and <i>m</i> -Xylene	57.3	56.5	43.3	20.8
<i>o</i> -Xylene	9.5	9.5	7.6	1.2
Indene	18.5	13.6	11.0	2.6
<i>Olefin selectivity</i>				
Ethylene	14.3	18.0	20.2	0
Propylene	43.7	50.2	51.5	100
Butenes	38.3	25.9	24.9	0
Butadiene	3.7	5.9	3.4	0

Fig. 5 Product yields as a function of temperature for catalytic conversion of methanol. Reaction conditions: ZSM-5 catalyst, 0.35 h⁻¹ WHSV, 1200 mL min⁻¹ helium fluidizing flow rate, 30 min reaction time. Key: (a) ■ Aromatics, ▲ C₂–C₄ Olefins, ● C₅ compounds, ◆ Unidentified; (b) □ Methane, △ CO₂, ○ CO, ◇ Coke.

high temperature (600 °C) almost all the methanol is converted into CO, CO₂, methane and coke.

3.2.2 Effect of weight hourly space velocity on product yields and selectivities. Fig. 6 and Table 4 show product yields as a function of WHSV for catalytic conversion of methanol at 450 °C. The petrochemical yields increase rapidly at lower WHSV, while CO, CO₂, methane and coke yields show the opposite trend. At WHSV above 0.50, little change is observed. The petrochemical yield increases from 19.5% to 59.7% when the WHSV increases from 0.08 h⁻¹ to 0.15 h⁻¹. The petrochemical yield increases to 71.5% at WHSV = 0.35 h⁻¹, however, further increasing the WHSV has little effect on the total yield. This indicates that methanol conversion is sensitive at low WHSV. Benzene selectivity decreases, and xylene selectivity increases with increasing WHSV. Ethylene selectivity decreases, and propylene and butenes selectivities increase with the increase of

Table 4 Detailed product yields and selectivities for catalytic conversion of methanol at various WHSV values and 450 °C. Aromatic selectivity is defined as the moles of carbon in the product divided by the total moles aromatic carbon. Olefin selectivity is defined as the moles of carbon in the product divided by the total moles olefin carbon

Compound	WHSV (h ⁻¹)				
	0.08	0.15	0.35	0.68	2.11
<i>Overall yields</i>					
Aromatics	2.8	9.7	11.1	14.0	13.5
C ₂ –C ₄ olefins	14.2	45.2	52.6	50.8	51.2
C ₅ compounds	2.6	4.8	7.9	12.7	14.2
Petrochemicals	19.5	59.7	71.5	77.5	78.9
Methane	9.9	10.5	4.5	3.6	2.2
CO ₂	27.8	12.0	8.9	7.0	3.0
CO	36.0	8.1	5.1	1.8	0.9
Coke	6.4	5.7	2.1	1.1	0.3
Total balance	99.7	95.9	92.1	90.9	85.3
Unidentified	0.3	4.1	7.9	9.1	14.7
<i>Aromatic selectivity</i>					
Benzene	9.2	3.8	3.3	2.9	2.2
Toluene	22.1	16.5	15.6	17.7	16.0
Ethyl-benzene	0	1.3	1.6	2.2	2.6
<i>p</i> -Xylene and <i>m</i> -Xylene	49.5	54.9	56.5	55.7	58.8
<i>o</i> -Xylene	13.1	10.2	9.5	9.8	9.2
Indene	6.2	13.2	13.6	11.6	11.3
<i>Olefin selectivity</i>					
Ethylene	35.0	17.3	18.0	14.9	12.6
Propylene	34.1	52.7	50.2	42.6	42.3
Butenes	27.7	25.3	25.9	37.4	43.2
Butadiene	3.2	4.7	5.9	5.1	1.9

Fig. 6 Product yields as a function of WHSV for catalytic conversion of methanol. Reaction conditions: ZSM-5 catalyst, 450 °C, 1200 mL min⁻¹ helium fluidizing flow rate, 30 min reaction time. Key: (a) ■ Aromatics, ▲ C₂–C₄ olefins, ● C₅ compounds, ◆ Unidentified; (b) □ Methane, △ CO₂, ○ CO, ◇ Coke.

WHSV. These experiments show that the maximum petrochemical yield for methanol conversion occurs at low temperatures and high WHSV.

3.3 Co-catalytic fast pyrolysis of pine wood and methanol

3.3.1 Effect of hydrogen to carbon effective (H/C_{eff}) ratio at 450 °C. CFP of pine wood and methanol mixtures was carried out by co-feeding them to the reactor. The H/C_{eff} ratio of the feed was adjusted by changing the space velocity ratio of pine wood and methanol. Based on our previous methanol and wood runs, we decided to operate the reactor at 450 °C and 500 °C. The product yields of co-CFP of pine wood and methanol at 450 °C as a function of H/C_{eff} ratio is shown in Fig. 7 and Table 5. The petrochemical yield increases non-linearly with increasing H/C_{eff} ratio. This curvature indicates that there is a synergistic effect between the feeds since pure addition of the yields would

Table 5 Detailed product yields and selectivities for co-CFP of pine wood and methanol at various H/C_{eff} ratios and 450 °C. Aromatic selectivity is defined as the moles of carbon in the product divided by the total moles aromatic carbon. Olefin selectivity is defined as the moles of carbon in the product divided by the total moles olefin carbon

Compound	H/C _{eff} (mol/mol) ratio						
	0.11	0.47	0.76	1.05	1.25	1.64	2.00
Pine wood WHSV (h ⁻¹)	0.35	0.46	0.23	0.28	0.20	0.06	0
Methanol WHSV (h ⁻¹)	0	0.13	0.15	0.35	0.37	0.34	0.35
Total WHSV (h ⁻¹)	0.35	0.59	0.38	0.63	0.56	0.41	0.35
Overall yields							
Aromatics	5.9	14.8	18.8	21.4	21.1	14.0	11.1
C ₂ –C ₄ olefins	4.3	13.5	18.7	26.4	32.9	47.9	52.6
C ₅ compounds	0.5	1.2	2.9	3.7	4.7	6.3	7.9
Petrochemicals	10.7	29.4	40.5	51.4	58.7	68.3	71.5
Methane	0.6	1.4	2.6	1.5	2.1	3.1	4.5
CO ₂	8.9	7.3	6.8	7.1	7.2	7.8	8.9
CO	19.7	14.9	12.6	9.4	7.7	5.8	5.1
Coke	41.6	30.3	23.4	17.8	14.5	7.4	2.1
Total balance	81.4	83.3	85.8	87.2	90.2	92.3	92.1
Unidentified	18.6	16.7	14.2	12.8	9.8	7.7	7.9
Theoretical petrochemical yield	64.3	71.2	76.6	82.2	85.8	93.2	100
Aromatic selectivity							
Benzene	10.8	6.5	6.7	5.8	5.8	4.5	3.3
Toluene	32.2	24.6	21.8	20.2	16.9	18.0	15.6
Ethyl-benzene	3.4	2.9	2.5	3.1	2.4	1.5	1.6
<i>p</i> -Xylene and <i>m</i> -Xylene	33.2	48.6	51.0	51.1	53.6	52.2	56.5
<i>o</i> -Xylene	4.8	8.2	9.2	11.4	9.3	11.3	9.5
Benzofuran	4.3	2.2	1.0	1.0	0.6	0.4	0
Indene	2.6	2.4	3.0	3.8	8.5	11.6	13.6
Phenol	1.1	0.4	0.3	0.2	0.2	0	0
Naphthalene	7.7	4.4	4.5	3.5	2.8	0.6	0
Olefin selectivity							
Ethylene	54.9	37.9	30.9	23.2	19.6	16.1	18.0
Propylene	36.0	40.1	44.4	48.7	50.3	51.4	50.2
Butenes	7.3	19.9	21.3	24.9	26.4	27.6	25.9
Butadiene	1.8	2.1	3.4	3.2	3.7	4.9	5.9

Fig. 7 Product yields as a function of H/C_{eff} ratio for co-CFP of pine wood and methanol at 450 °C. Key: (a) ■ Aromatics, ▲ C₂–C₄ olefins, ● C₅ compounds, ◆ Unidentified, * Petrochemicals; (b) □ Methane, △ CO₂, ○ CO, ◇ Coke.

yield a straight line with increasing H/C_{eff} ratio. This synergistic effect of co-feeding is very apparent in the aromatic yield. The aromatic yield is 5.9% for the only pine wood run and 11.1% in the only methanol run. However, at the intermediate value of $H/C_{\text{eff}} = 1.05$, a maximum yield of 21.4% aromatics is realized. This result indicates that the aromatic yield is enhanced by co-feeding methanol and is not purely additive. The unidentified oxygenates yield decreases from 18.6% at $H/C_{\text{eff}} = 0.11$ to

7.9% at $H/C_{\text{eff}} = 2$. As shown in Fig. 7(b), the yields of CO and coke decrease significantly with the increase of the H/C_{eff} ratio as non-linear curves, while that of CO₂ remains constant. Fig. 8 shows the selectivities of benzene, toluene, xylene and naphthalene in the aromatic products and ethylene, propylene, butenes and butadiene in olefin products. As shown in the figure, the selectivities of the more valuable chemicals, such as xylene, propylene, butenes and butadiene, increase significantly with the increase of H/C_{eff} ratio, while the selectivities of the less valuable chemicals, such as naphthalene decreases.

Fig. 8 Main aromatics and C₂–C₄ olefins selectivities as a function of H/C_{eff} ratio for co-CFP of pine wood and methanol at 450 °C. (a) ■ Benzene, ▲ Toluene, ● Xylene, ◆ Naphthalene; (b) □ Ethylene, △ Propylene, ○ Butenes, ◇ Butadiene.

3.3.2 Effect of hydrogen to carbon effective (H/C_{eff}) ratio at 500 °C. The product carbon yields and selectivities as a function of H/C_{eff} ratio for co-CFP of pine wood and methanol at 500 °C are shown in Fig. 9 and 10 and Table 6. It can be seen from Fig. 9 that the unidentified compounds, CO and coke yields decrease with the increasing H/C_{eff} ratio, while C₂–C₄ olefins, CO₂ and methane yields increase significantly. Aromatic yield is relatively constant at around 10% when the H/C_{eff} ratio increases from 0.11 to 1.15. The aromatic yield decreases to 5.5% with further increase of the H/C_{eff} ratio to 2. As shown in Fig. 10, xylene selectivity increases with increasing H/C_{eff} ratio, and toluene selectivity decreases. Propylene selectivity increases with increasing H/C_{eff} ratio. Ethylene selectivity decreases non-linearly with the increasing of the H/C_{eff} ratio, whereas butenes selectivity shows the opposite trend and increases non-linearly. These non-linear curves indicate that the products are affected by the co-feeding, and again a synergistic effect occurs at 500 °C.

Fig. 9 Product yields as a function of H/C_{eff} ratio for co-CFP of pine wood and methanol at 500 °C. Key: (a) ■ Aromatics, ▲ C₂–C₄ olefins, ● C₅ compounds, ◆ Unidentified, * Petrochemicals; (b) □ Methane, △ CO₂, ○ CO, ◇ Coke.

3.3.3 Effect of the total space velocity at constant H/C_{eff} ratio. Fig. 11 and 12 show the product carbon yields and

Table 6 Detailed product yields and selectivities for co-CFP of pine wood and methanol at various H/C_{eff} ratios and 500 °C. Aromatic selectivity is defined as the moles of carbon in the product divided by the total moles aromatic carbon. Olefin selectivity is defined as the moles of carbon in the product divided by the total moles olefin carbon

Compound	H/C_{eff} ratio (mol/mol)				
	0.11	0.51	0.74	1.15	2.00
Pine wood WHSV (h^{-1})	0.41	0.24	0.28	0.18	0
Methanol WHSV (h^{-1})	0	0.08	0.18	0.27	0.35
Total WHSV (h^{-1})	0.41	0.33	0.46	0.44	0.35
<i>Overall yields</i>					
Aromatics	10.5	10.3	10.6	9.6	5.5
C_2 – C_4 olefins	5.4	11.1	13.5	21.1	34.6
C_5 compounds	0.3	1.2	1.3	1.1	1.8
Petrochemicals	16.2	22.6	25.4	31.8	41.9
Methane	2.1	4.3	5.5	8.0	11.0
CO_2	7.7	9.8	14.1	17.3	21.5
CO	25.6	24.0	23.7	21.8	21.0
Coke	31.7	24.6	20.1	12.7	2.9
Total balance	83.3	85.3	88.7	91.5	98.3
Unidentified	16.7	14.7	11.3	8.5	1.7
Theoretical petrochemical yield	64.3	72.0	76.2	83.9	100
<i>Aromatic selectivity</i>					
Benzene	15.3	11.7	10.6	10.6	9.7
Toluene	34.7	28.5	27.7	26.9	19.3
Ethyl-benzene	4.5	2.2	2.3	1.9	2.5
<i>p</i> -Xylene and <i>m</i> -Xylene	24.1	28.8	33.6	41.8	43.3
<i>o</i> -Xylene	3.5	0.9	0.8	7.6	7.7
Styrene	3.7	5.2	6.2	0	4.4
Benzofuran	1.6	9.0	7.7	2.8	0
Indene	3.3	2.0	1.7	1.2	11.0
Phenol	1.5	1.0	0.8	0.5	0
Naphthalene	7.7	10.8	8.6	6.7	2.2
<i>Olefin selectivity</i>					
Ethylene	49.0	33.2	26.5	24.1	20.2
Propylene	37.8	41.9	44.1	46.3	51.5
Butenes	7.0	20.9	24.8	25.5	24.9
Butadiene	6.2	4.0	4.6	4.1	3.4

Fig. 10 Main aromatics and C_2 – C_4 olefins selectivities as a function of H/C_{eff} ratio for co-CFP of pine wood and methanol at 500 °C. (a) ■ Benzene, ▲ Toluene, ● Xylene, ◆ Naphthalene; (b) □ Ethylene, △ Propylene, ○ Butenes, ◇ Butadiene.

selectivities of co-CFP of pine wood and methanol at different total WHSV with a constant H/C_{eff} ratio of 1.05 at 450 °C. It can be seen from Fig. 11, lower total WHSV favors C_2 – C_4 olefins and coke productions, while higher WHSV produces more CO and unidentified oxygenates. The aromatic and total petrochemical yields go through a maximum value of 21.4% and 51.4% at a WHSV of 0.63 h^{-1} , respectively. The aromatic and olefin selectivities are relatively constant over the WHSV range tested, with the exception of toluene and butenes that increase slightly with WHSV. Table 7 shows the detailed product carbon

Table 7 Detailed product yields and selectivities for co-CFP of pine wood and methanol at various total space velocities, $H/C_{\text{eff}} = 1.05$ and 450 °C. Aromatic selectivity is defined as the moles of carbon in the product divided by the total moles aromatic carbon. Olefin selectivity is defined as the moles of carbon in the product divided by the total moles olefin carbon

Compound	Total WHSV (h^{-1})		
	0.27	0.63	1.33
$T/^\circ\text{C}$	450	450	450
Pine wood WHSV (h^{-1})	0.12	0.28	0.65
WHSV of co-feeding alcohol (h^{-1})	0.15	0.35	0.68
H/C_{eff} (mol/mol)	1.05	1.05	0.98
<i>Overall yields</i>			
Aromatics	17.1	21.4	18.9
C_2 – C_4 olefins	27.6	26.3	21.5
C_5 compounds	2.4	3.7	2.8
Petrochemicals	47.1	51.4	43.2
Methane	2.2	1.5	1.3
CO_2	6.6	7.1	4.6
CO	8.9	9.4	12.8
Coke	23.6	17.8	16.4
Total balance	88.4	87.2	78.2
Unidentified	11.6	12.8	21.8
Theoretical petrochemical yield	82.2	82.2	80.8
<i>Aromatic selectivity</i>			
Benzene	3.8	5.8	4.3
Toluene	16.5	20.2	21.0
Ethyl-benzene	1.8	3.1	3.6
<i>p</i> -Xylene and <i>m</i> -Xylene	49.8	51.1	51.6
<i>o</i> -Xylene	9.6	11.4	9.0
Benzofuran	1.8	1.0	0.5
Indene	13.2	3.8	7.0
Phenol	0.5	0.2	0.2
Naphthalene	3.0	3.5	2.9
<i>Olefin selectivity</i>			
Ethylene	24.3	23.2	24.3
Propylene	52.9	48.7	48.3
Butenes	19.5	24.9	24.1
Butadiene	3.3	3.2	3.3

Fig. 11 Product carbon yields of co-CFP of pine wood and methanol at different total WHSV values, $H/C_{\text{eff}} = 1.05$ and 450 °C. Key: (a) ■ Aromatics, ▲ C_2 – C_4 olefins, ● C_5 compounds, ◆ Unidentified; (b) □ Methane, △ CO_2 , ○ CO , ◇ Coke.

yields and selectivities for co-CFP of pine wood and methanol at different total space velocities.

3.3.4 Isotopic labelling studies of co-catalytic fast pyrolysis of pine wood and methanol. Co-CFP of ^{12}C pine wood and isotopically labeled ^{13}C methanol was conducted at 450 °C to determine how methanol enters the hydrocarbon pool. The WHSV values of ^{12}C pine wood and ^{13}C methanol were 0.30 h^{-1} and 0.29 h^{-1} , respectively. The H/C_{eff} ratio of the mixture was 0.97. The mass spectra of the most abundant products are shown in Fig. 13. The fragmentation patterns for the pure

Fig. 12 Main aromatics and C₂–C₄ olefins selectivities of co-CFP of pine wood and methanol at different total WHSV values, H/C_{eff} = 1.05 and 450 °C. (a) ■ Benzene, ▲ Toluene, ● Xylene, ◆ Naphthalene; (b) □ Ethylene, △ Propylene, ○ Butenes ◇ Butadiene.

¹²C or pure ¹³C compounds are shown in black and white, respectively. The spectra of the product obtained during the co-feeding experiment are shown in grey. The results show that all the main products are a mixture of ¹²C and ¹³C labeled carbons. The distribution of carbon in benzene is a random mixture of the ¹²C and ¹³C carbons. However, the distributions of carbon within the other aromatics show trends. The distribution of toluene and xylene are both shifted to the higher masses. This indicates that a randomly distributed benzene molecule was preferably alkylated by a ¹³C-containing radical over a ¹²C-containing radical. Naphthalene shows the opposite trend as its spectrum is shifted toward the lower masses. This shows that the rate of naphthalene formation from the pine wood is higher than that from the methanol. The methyl naphthalene is not as shifted as the naphthalene, which shows that the methyl group probably also came from methanol, similar to toluene and xylene. The olefin compounds spectra also show obvious trends. When taking into account the overlap of the fragmentation peaks, the ethylene appears to be composed of more ¹²C than ¹³C carbon, while propylene and butenes show more ¹³C carbon. In summary, ¹²C and ¹³C are distributed in all the hydrocarbon product molecules. Benzene is a random mixture of the ¹²C and ¹³C carbons, whereas naphthalene is formed much faster from the carbon of pine wood than methanol. However, their alkylated products were preferably alkylated by a ¹³C-containing radical over a ¹²C-containing radical. This indicates that the methanol enters zeolite catalytic process of biomass and it is feasible to use feeds with high H/C_{eff} ratio to provide hydrogen to the hydrocarbon pool for biomass conversion.

3.4 Co-catalytic fast pyrolysis of other alcohols

Fig. 14 and Table 8 shows the petrochemical yield of co-CFP of pine wood and other alcohols at H/C_{eff} = 1.25 and 450 °C. The “calculated” values for the mixtures were found by a weighted average of the yields from CFP of pine wood and the alcohol separately. As shown in the figure, CFP of pine wood produced 10.7% hydrocarbon yield, while methanol, 1-propanol, 1-butanol and 2-butanol gave 71.5%, 86.8%, 86.3% and 90.3% of hydrocarbon yield, respectively. The co-feeding of pine wood and methanol yielded the lowest amount of petrochemicals (58.7%), while co-feeding of pine wood and 2-butanol produced the highest carbon yield of 65.2%. However, compared with their calculated values, co-CFP of pine wood and methanol gave the highest increase of hydrocarbon yield

Fig. 13 Isotopic distributions for benzene, toluene, xylene, naphthalene, 1-methyl naphthalene, ethylene, propylene and 1-butene from the co-CFP of ¹²C pine wood and ¹³C methanol. Pure ¹²C and ¹³C mass spectra for the given molecules are shown in black and white, respectively. The co-feeding run results are shown in grey. Reaction conditions: catalyst, ZSM-5; reaction temperature, 450 °C; WHSV of ¹²C pine wood, 0.30 h⁻¹; WHSV of ¹³C methanol, 0.29 h⁻¹; the hydrogen to carbon effective (H/C_{eff}) ratio, 0.97; helium fluidizing flow rate, 1200 mL min⁻¹; reaction time, 30 min.

and the best synergistic effect. The product carbon yields and selectivities of co-CFP of pine wood and the various alcohols at H/C_{eff} = 1.25 and 450 °C are listed in Table 8. As shown in the table, the product selectivities of co-CFP of pine wood and 1-propanol, 1-butanol and 2-butanol are very similar, but there is a great difference with co-feeding pine wood and methanol, especially in aromatic selectivities. Co-conversion of pine wood and methanol gave 62.9%, 5.8% and 16.9% selectivities of xylene, benzene and toluene, respectively. Co-conversion of pine wood with other alcohols gave about 39.2–40.2%, 10.4–11.0% and 38.6–39.3% of xylene, benzene and toluene, respectively. This can be explained by the fact that methanol produced more methyl radicals than other alcohols at the same H/C_{eff} ratio. Thus more benzene and toluene molecules were alkylated to xylene molecules.

Table 8 Detailed product yields and selectivities for CFP of pine wood and methanol, 1-propanol, 1-butanol and 2-butanol at $H/C_{\text{eff}} = 1.25$ and 450°C . Aromatic selectivity is defined as the moles of carbon in the product divided by the total moles aromatic carbon. Olefin selectivity is defined as the moles of carbon in the product divided by the total moles olefin carbon

Compound	Co-feeding alcohol								
	Pine wood	Methanol	1-Propanol	1-Butanol	2-Butanol				
Pine wood WHSV (h^{-1})	0.35	0	0.20	0	0.24	0	0.30	0	0.29
WHSV of co-feeding alcohol (h^{-1})	0	0.35	0.36	0.34	0.34	0.34	0.34	0.35	0.35
Total WHSV (h^{-1})	0.35	0.35	0.56	0.34	0.58	0.34	0.64	0.35	0.64
H/C_{eff} ratio (mol/mol)	0.11	2.00	1.25	2.00	1.34	2.00	1.27	2.00	1.31
<i>Overall yields</i>									
Aromatics	5.9	11.1	21.1	13.3	16.3	15.2	17.2	15.2	15.6
C_2 – C_4 olefins	4.3	52.6	32.9	66.2	43.3	60.7	38.4	67.2	44.6
C_5 compounds	0.5	7.9	4.7	7.3	4.6	10.3	6.0	7.9	5.0
Petrochemicals	10.7	71.5	58.7	86.8	64.3	86.3	61.5	90.3	65.2
Methane	0.6	4.5	2.1	0.2	0.4	0.2	0.4	0.2	0.4
CO_2	8.9	8.9	7.2	0.2	2.3	0.2	2.2	0.2	2.8
CO	19.7	5.1	7.7	0.4	6.5	1.1	6.9	0.5	7.6
Coke	41.6	2.1	14.5	1.6	10.7	1.0	14.3	1.0	12.8
Total balance	81.4	92.1	90.2	89.2	84.1	88.7	85.5	92.1	88.8
Theoretical (Toluene)	64.3	100	85.8	100	87.5	100	86.2	100	86.9
Experimental/theoretical	16.6	71.5	68.4	86.8	73.5	86.3	71.4	90.3	75.0
<i>Aromatic selectivity</i>									
Benzene	10.8	3.3	5.8	11.8	11.0	11.5	10.6	12.0	10.4
Toluene	32.2	15.6	16.9	43.1	39.3	40.8	38.7	43.8	38.6
Ethyl-benzene	3.4	1.6	2.4	3.6	3.7	3.5	4.2	3.7	4.2
<i>p</i> -Xylene and <i>m</i> -Xylene	33.2	56.5	53.6	31.0	32.8	27.9	34.2	30.5	34.0
<i>o</i> -Xylene	4.8	9.5	9.3	7.0	6.4	6.0	6.0	6.7	6.2
Benzofuran	4.3	0	0.6	0.1	0.5	0.1	0.5	0.1	0.4
Indene	2.6	13.6	8.5	2.5	2.3	2.0	2.5	2.3	2.6
Phenol	1.1	0	0.2	0.2	0.5	0.1	0.2	0.2	0.5
Naphthalene	7.7	0	2.8	0.8	3.6	0.6	3.1	0.7	3.1
<i>Olefin selectivity</i>									
Ethylene	54.9	18.0	19.5	10.9	12.8	12.2	12.4	10.0	13.4
Propylene	36.0	50.2	50.3	55.7	54.5	52.7	53.8	53.8	51.5
Butenes	7.3	25.9	26.5	29.6	28.6	31.4	29.8	32.6	30.9
Butadiene	1.8	5.9	3.7	3.8	4.1	3.7	4.0	3.6	4.2

Fig. 14 The petrochemical yield of co-CFP of pine wood and methanol, 1-propanol, 1-butanol and 2-butanol at $H/C_{\text{eff}} = 1.25$ and 450°C . Key: $\diagup$ Pure pine wood; — Experimental values for co-feeding of pine wood with alcohol; — Calculated values of co-feeding of pine wood with alcohols; — Pure alcohol.

4. Discussions

4.1 Comparison of products of co-catalytic fast pyrolysis of pine wood and methanol at 450°C and 500°C

Fig. 15 shows the petrochemical yield as a function of H/C_{eff} ratio for co-CFP of pine wood and methanol at 450°C and 500°C . As shown in the figure, co-CFP of pine wood and

Fig. 15 The petrochemical yield as a function of H/C_{eff} ratio at 450°C and 500°C . Key: Petrochemical experimental yield at reaction temperature of $\blacksquare$ 450°C and $*$ 500°C ; $\blacktriangle$ Theoretical yield; Experimental/theoretical ratio at reaction temperature of $\circ$ 450°C , $\diamond$ 500°C .

methanol at 450°C produced much more petrochemicals than that at 500°C , and the gap increases with increasing H/C_{eff} ratio. The theoretical yields of dry pine wood and methanol are calculated by assuming toluene as the reaction hydrocarbon product. The calculating equations are shown in eqn (2) and (3).

The theoretical yield of dry pine wood is about 67% carbon according to eqn (2), while that of methanol is 100% carbon shown in eqn (3). The pine wood used in this study contains about 4% moisture, thus the theoretical yield of pine wood based on the feed is 64.3%. The theoretical yield plot in Fig. 15 is drawn according to the theoretical yields that would be achieved if all the carbon in the biomass is converted into toluene, water, and carbon monoxide. Data points are added to this based on our previous study, which used ten different feedstocks.⁵⁸

Also included in Fig. 15 is the ratio of experimental to the theoretical (experimental/theoretical) yield of the different feedstocks. This ratio allows us to determine how close to the theoretical carbon yield we are for each experiment. At 450 °C, this ratio increases non-linearly from 16.6% at $\text{H}/\text{C}_{\text{eff}} = 0.11$ (only pine wood) to about 70% at $\text{H}/\text{C}_{\text{eff}} = 1.25$. Further increasing the $\text{H}/\text{C}_{\text{eff}}$ ratio above 1.25 only gives a small change in the experimental/theoretical ratio. This result suggests that the co-feeding of wood and methanol allows us to more efficiently convert the carbon in these feedstocks into petrochemicals by co-feeding rather than feeding the two reactants separately. Furthermore, the $\text{H}/\text{C}_{\text{eff}}$ ratio = 1.25 is an inflection point, where the petrochemical yield does not increase as rapidly. This result is consistent with our previous study in which we catalytically deoxygenated ten biomass-derived feedstocks with different $\text{H}/\text{C}_{\text{eff}}$ ratios with a zeolite catalyst and found an $\text{H}/\text{C}_{\text{eff}}$ ratio = 1.2 to be the inflection point.⁵⁸ This suggests that the amount of methanol co-fed with pine wood should be enough to bring the mixtures to an $\text{H}/\text{C}_{\text{eff}}$ ratio of 1.25. It should be noted that co-CFP can not run at high temperature since methanol would be converted into CO, CO₂, methane and coke at high temperature and pine wood would be converted into coke and unidentified oxygenates with this catalyst. The suitable temperature for co-CFP of pine wood and methanol is 450 °C.

Although co-feeding pine wood and methanol at 450 °C produced much more petrochemicals than reacting the two feeds at 450 °C separately, the petrochemical yield of co-feeding is still lower than running the two feeds at their optimal temperatures (pine wood: 600 °C; methanol: 400 °C). Therefore, to be more effective at co-utilization of wood and methanol, the catalyst should be designed to decrease the optimal temperature of pine wood CFP or increase that of methanol conversion.

4.2 Chemistry of co-catalytic fast pyrolysis of pine wood and methanol

Co-feeding of ¹²C pine wood and ¹³C methanol results show that all the hydrocarbon products contained ¹²C and ¹³C in their molecules. Our previous results observed this same phenomenon with a 1:1 w/w mixture of pure ¹²C and ¹³C glucose as reactants.⁷⁸ This suggests that the feeds (or their derived/pyrolysis products) enter the zeolite catalyst, lose their identity within a hydrocarbon pool and combine stochastically with other molecules. This proves that adding hydrogen to biomass conversion process *via* co-feeding it with other higher $\text{H}/\text{C}_{\text{eff}}$ ratio feeds is feasible.

From the isotopic distribution of benzene, we can see that the amount of ¹²C and ¹³C is almost the same in the benzene molecule. The toluene and xylene are probably produced from alkylation of benzene. However, their isotopic distributions are not normal distributions and lean to ¹³C. Combining this with benzene's isotopic distribution, it seems that almost all the methyl radicals for benzene alkylation are from methanol. Our previous study showed that naphthalene is formed by monocyclic aromatics with oxygenated fragments that are the derived products of biomass pyrolysis.⁷⁸ The isotopic distribution of naphthalene, shown in Fig. 15, agrees with this conclusion because the distribution is skewed to ¹²C. In this study, the naphthalene is produced by randomly formed benzene combining with the oxygenated fragments (usually that are based on a furanic structure) that are the derived products of biomass pyrolysis. Methanol makes almost no naphthalene in the separate and co-feeding it with pine wood runs. Compared with the isotopic distribution of naphthalene, 1-methyl naphthalene distribution leans to ¹³C by 1 carbon. Thus methanol is also able to alkylate naphthalene.

4.3 Economic potential

In Section 3.3.1 it was shown that co-feeding pine wood and methanol at 450 °C increases the total aromatic yield. However, the total petrochemical yield is always highest for the pure compounds. A simple economic analysis is done to determine whether co-feeding methanol with wood is economically beneficial with the conditions used in this paper. The economic potential (EP) was used to evaluate the potential economic benefit of co-feeding wood with methanol. The EP is calculated by eqn (4):

$$\text{EP} = \Sigma \text{price of products} - \Sigma \text{price of feeds} \quad (4)$$

EP is calculated for the different temperatures used in this paper. The scale of the refinery was set at 250,000 tons products/year for all these calculations. Wood and methanol prices usually range between \$20–100/ton¹ and \$260–360/ton,⁷⁹ respectively. Five groups of price combinations were used for comparison to allow us to determine the sensitivity of these different scenarios with feedstock prices. These five groups are (a) low methanol price and low wood price, (b) high methanol price and high wood price, (c) low methanol price and high wood price, (d) high methanol price and low wood price and (e) medium methanol price and medium wood price. These figure groups of price combinations are shown in Fig. 16a–e. Each figure also shows the results with pure wood and pure methanol. The product prices were based on the following values: \$889/ton-benzene, \$735/ton-toluene, \$1521/ton-styrene, \$690/ton-indene, \$690/ton-naphthalene, \$804/ton-mixed xylenes, \$970/ton-ethylene, \$1212/ton-propylene, \$1200/ton-butenes, \$2270/ton-butadiene and \$690/ton-gasoline (C₅ compounds).⁷⁹

As can be seen from Fig. 16, co-feeding pine wood and methanol at a reaction temperature of 450 °C gives a higher EP than at a reaction temperature of 500 °C for all price scenarios when the $\text{H}/\text{C}_{\text{eff}}$ ratio of the feed is greater than or equal to 0.50. When wood price is low (Fig. 16a), the EP is highest when pure wood is added to the reactor. When wood price is high,

Fig. 16 Economic potential (EP) for CFP and co-CFP of wood and methanol as a function of H/C_{eff} ratio at different feed prices. Price for wood (W) and methanol (M) (\$/metric ton): (a) W = 20, M = 267; (b) W = 100, M = 334; (c) W = 20, M = 334; (d) W = 100, M = 267; (e) W = 60, M = 300. Key: ■ Co-feeding of pine wood and methanol at 500 °C; ◆ Co-feeding of pine wood and methanol at 450 °C; ▲ Pine wood at 600 °C; ● Methanol at 400 °C.

co-feeding pine wood and methanol at 450 °C made the EP increase non-linearly with increasing H/C_{eff} ratio (see Fig. 16(b, d and e)). This considerable curvature indicates that co-feeding

of pine wood and methanol has much higher EP than that of running them separately. However, the EP of co-feeding pine wood and methanol is still lower than that of running them separately at their optimal conditions (pine wood: 600 °C and 0.35 h⁻¹; methanol: 400 °C and 0.35 h⁻¹).

5. Conclusions

In this work, we conducted catalytic fast pyrolysis (CFP) of pine wood, alcohols (methanol, 1-propanol, 1-butanol and 2-butanol) and their mixtures with ZSM-5 catalyst in a fluidized bed reactor. The maximum petrochemical yield when pine wood was the feedstock was 23.7%, which occurred at 600 °C and 0.35 h⁻¹. Both the coke and unidentified oxygenates yields decrease with increasing temperature, whereas the coke yield decreases and the unidentified oxygenates yield increases with increasing WHSV. The maximum petrochemical yield when methanol was the feed was 80.7% and occurred at 400 °C and 0.35 h⁻¹. The yields of petrochemicals and unidentified compounds decrease with increasing temperature, and the yields of methane, CO₂, CO and coke increase with the increasing temperature. The petrochemical yields increase rapidly at lower WHSV, while CO, CO₂, methane and coke yields show the opposite trend.

CFP of pine wood and methanol mixtures with different ratios were tested at 450 °C and 500 °C. The results show that the petrochemical yield increases non-linearly with increasing H/C_{eff} ratio of the feed, and more petrochemicals can be produced from wood when methanol is added to the CFP process. $H/C_{\text{eff}} = 1.25$ is an inflection point in this process, where the petrochemical yield begins to reach an asymptote. This suggests that the amount of methanol co-fed with wood should be enough to bring the mixtures to an H/C_{eff} ratio of 1.25. Adding more methanol would be a waste of methanol and increase the cost of the process, since methanol price is much higher than wood's. Co-CFP of pine wood and other alcohols also increases the petrochemical yield, whereas co-CFP of pine wood and methanol gave the highest increase of petrochemical yield.

The isotopic studies of CFP with ¹²C methanol and ¹³C pine wood showed that the products were produced from mixtures of methanol and pine wood. Benzene was made from random mixtures of methanol and pine wood. Propylene and butenes were produced more from methanol than wood. Naphthalene contained more ¹²C and therefore were produced more from pine wood than methanol. This indicates that it is feasible to use feeds with high H/C_{eff} ratio to provide hydrogen to the hydrocarbon pool for biomass conversion.

In summary, the petrochemical yield produced by CFP of biomass can be enhanced by co-feeding it with feeds that have a high H/C_{eff} ratio. In the co-feeding process, the two feeds can be converted together within the zeolite and have a positive synergistic effect. This study provides insights into how biomass resources can be used more efficiently to produce renewable petrochemicals. It is likely that future advances in the design of improved catalysts combined with reaction engineering will lead to the design of even more efficient processes for the production of renewable fuels and chemicals.

Acknowledgements

The authors are grateful for the U. S. National Science Foundation (Grant No. EFRI-0937895), National Basic Research Program of China (973 Program, Grant No. 2010CB732206), National Natural Science Foundation of China (Grant No. 51076031), China Scholarship Council and the Scientific Research Foundation of Graduate School of Southeast University.

References

- 1 G. W. Huber, S. Iborra and A. Corma, *Chem. Rev.*, 2006, **106**, 4044–4098.
- 2 E. L. Kunkes, D. A. Simonetti, R. M. West, J. C. Serrano-Ruiz, C. A. Gartner and J. A. Dumesic, *Science*, 2008, **322**, 417–421.
- 3 S. Czernik, J. Scahill and J. Diebold, *J. Sol. Energy Eng.*, 1995, **117**, 2–6.
- 4 A. V. Bridgwater, *Int. J. Global Energy Issues*, 2007, **27**, 160–203.
- 5 A. Demirbas, *Energy Convers. Manage.*, 2001, **42**, 1357–1378.
- 6 M. Olazar, R. Aguado, J. Bilbao and A. Barona, *AIChE J.*, 2000, **46**, 1025–1033.
- 7 G. W. Huber and A. Corma, *Angew. Chem., Int. Ed.*, 2007, **46**, 7184–7201.
- 8 R. French and S. Czernik, *Fuel Process. Technol.*, 2010, **91**, 25–32.
- 9 M. Stocker, *Angew. Chem., Int. Ed.*, 2008, **47**, 9200–9211.
- 10 Y. C. Lin and G. W. Huber, *Energy Environ. Sci.*, 2009, **2**, 68–80.
- 11 M. Garcia-Perez, X. S. Wang, J. Shen, M. J. Rhodes, F. J. Tian, W. J. Lee, H. W. Wu and C. Z. Li, *Ind. Eng. Chem. Res.*, 2008, **47**, 1846–1854.
- 12 D. Mohan, C. U. Pittman and P. H. Steele, *Energy Fuels*, 2006, **20**, 848–889.
- 13 D. A. Laird, R. C. Brown, J. E. Amonette and J. Lehmann, *Biofuels, Bioprod. Biorefin.*, 2009, **3**, 547–562.
- 14 C. J. Deng, R. H. Liu and J. M. Cai, *J. Energy. Inst.*, 2008, **81**, 211–217.
- 15 H. Y. Zhang, R. Xiao, D. H. Wang, G. Y. He, S. S. Shao, J. B. Zhang and Z. P. Zhong, *Bioresour. Technol.*, 2011, **102**, 4258–4264.
- 16 R. C. Saxena, D. K. Adhikari and H. B. Goyal, *Renewable Sustainable Energy Rev.*, 2009, **13**, 156–167.
- 17 M. F. Demirbas and M. Balat, *J. Sci. Ind. Res.*, 2007, **66**, 797–804.
- 18 R. D. Cortright, R. R. Davda and J. A. Dumesic, *Nature*, 2002, **418**, 964–967.
- 19 G. W. Huber, J. N. Chheda, C. J. Barrett and J. A. Dumesic, *Science*, 2005, **308**, 1446–1450.
- 20 T. P. Vispute and G. W. Huber, *Green Chem.*, 2009, **11**, 1433–1445.
- 21 R. Xing, A. V. Subrahmanyam, H. Olcay, W. Qi, G. P. van Walsum, H. Pendse and G. W. Huber, *Green Chem.*, 2010, **12**, 1933–1946.
- 22 N. Li and G. W. Huber, *J. Catal.*, 2010, **270**, 48–59.
- 23 N. Li, G. A. Tompsett, T. Y. Zhang, J. Shi, C. E. Wyman and G. W. Huber, *Green Chem.*, 2011, **13**, 91–101.
- 24 R. Luque, J. H. Clark, K. Yoshida and P. L. Gai, *Chem. Commun.*, 2009, 5305–5307.
- 25 J. P. Diebold and J. W. Scahill, *ACS Symp. Ser.*, 1988, **376**, 264–276.
- 26 J. Adam, E. Antonakou, A. Lappas, M. Stocker, M. H. Nilsen, A. Bouzga, J. E. Hustad and G. Oye, *Microporous Mesoporous Mater.*, 2006, **96**, 93–101.
- 27 E. Antonakou, A. Lappas, M. H. Nilsen, A. Bouzga and M. Stocker, *Fuel*, 2006, **85**, 2202–2212.
- 28 E. F. Iliopoulou, E. V. Antonakou, S. A. Karakoulia, I. A. Vasalos, A. A. Lappas and K. S. Triantafyllidis, *Chem. Eng. J.*, 2007, **134**, 51–57.
- 29 E. Putun, B. B. Uzun and A. E. Putun, *Energy Fuels*, 2009, **23**, 2248–2258.
- 30 C. N. Hamelinck, A. P. C. Faaij, H. den Uil and H. Boerrigter, *Energy*, 2004, **29**, 1743–1771.
- 31 M. J. A. Tijmensen, A. P. C. Faaij, C. N. Hamelinck and M. R. M. van Hardeveld, *Biomass Bioenergy*, 2002, **23**, 129–152.
- 32 D. L. Klass, *Fuels and Chemicals*, Academic Press, San Diego, CA, 1998.
- 33 B. Donniss, R. G. Egeberg, P. Blom and K. G. Knudsen, *Top. Catal.*, 2009, **52**, 229–240.
- 34 D. C. Elliott, *Energy Fuels*, 2007, **21**, 1792–1815.
- 35 J. Wildschut, M. Iqbal, F. H. Mahfud, I. M. Cabrera, R. H. Venderbosch and H. J. Heeres, *Energy Environ. Sci.*, 2010, **3**, 962–970.
- 36 J. D. Adjaye and N. N. Bakhshi, *Fuel Process. Technol.*, 1995, **45**, 161–183.
- 37 J. D. Adjaye and N. N. Bakhshi, *Fuel Process. Technol.*, 1995, **45**, 185–202.
- 38 B. Valle, A. G. Gayubo, A. Alonso, A. T. Aguayo and J. Bilbao, *Appl. Catal., B*, 2010, **100**, 318–327.
- 39 B. Valle, A. G. Gayubo, A. T. Aguayo, M. Olazar and J. Bilbao, *Energy Fuels*, 2010, **24**, 2060–2070.
- 40 A. G. Gayubo, B. Valle, A. T. Aguayo, M. Olazar and J. Bilbao, *Ind. Eng. Chem. Res.*, 2010, **49**, 123–131.
- 41 A. G. Gayubo, A. T. Aguayo, A. Atutxa, B. Valle and J. Bilbao, *J. Chem. Technol. Biotechnol.*, 2005, **80**, 1244–1251.
- 42 T. Q. Hoang, X. L. Zhu, L. L. Lobban, D. E. Resasco and R. G. Mallinson, *Catal. Commun.*, 2010, **11**, 977–981.
- 43 T. Q. Hoang, X. L. Zhu, T. Danuthai, L. L. Lobban, D. E. Resasco and R. G. Mallinson, *Energy Fuels*, 2010, **24**, 3804–3809.
- 44 T. Danuthai, S. Jongpatiwut, T. Rirksomboon, S. Osuwan and D. E. Resasco, *Appl. Catal., A*, 2009, **361**, 99–105.
- 45 A. Ausavasukhi, T. Sooknoi and D. E. Resasco, *J. Catal.*, 2009, **268**, 68–78.
- 46 A. Corma, G. W. Huber, L. Sauvanaud and P. O'Connor, *J. Catal.*, 2007, **247**, 307–327.
- 47 T. R. Carlson, T. R. Vispute and G. W. Huber, *ChemSusChem*, 2008, **1**, 397–400.
- 48 T. R. Carlson, Y. T. Cheng, J. H. Jae and G. W. Huber, *Energy Environ. Sci.*, 2011, **4**, 145–161.
- 49 J. H. Jae, G. A. Tompsett, Y. C. Lin, T. R. Carlson, J. C. Shen, T. Y. Zhang, B. Yang, C. E. Wyman, W. C. Conner and G. W. Huber, *Energy Environ. Sci.*, 2010, **3**, 358–365.
- 50 F. A. Agblevor, O. Mante, N. Abdoulmoumine and R. McClung, *Energy Fuels*, 2010, **24**, 4087–4089.
- 51 A. A. Lappas, M. C. Samolada, D. K. Iatridis, S. S. Voutetakis and I. A. Vasalos, *Fuel*, 2002, **81**, 2087–2095.
- 52 F. A. Agblevor, S. Beis, O. Mante and N. Abdoulmoumine, *Ind. Eng. Chem. Res.*, 2010, **49**, 3533–3538.
- 53 H. Y. Zhang, R. Xiao, H. Huang and G. Xiao, *Bioresour. Technol.*, 2009, **100**, 1428–1434.
- 54 H. Y. Zhang, R. Xiao, D. H. Wang, Z. P. Zhong, M. Song, Q. W. Pan and G. Y. He, *Energy Fuels*, 2009, **23**, 6199–6206.
- 55 A. Aho, N. Kumar, K. Eranen, T. Salmi, M. Hupa and D. Y. Murzin, *Process Saf. Environ. Prot.*, 2007, **85**, 473–480.
- 56 R. Luque, L. Herrero-Davila, J. M. Campelo, J. H. Clark, J. M. Hidalgo, D. Luna, J. M. Marinas and A. A. Romero, *Energy Environ. Sci.*, 2008, **1**, 542–564.
- 57 N. Y. Chen, J. T. F. Degnan and L. R. Koenig, *Chem. Tech.*, 1986, **16**, 506.
- 58 H. Y. Zhang, Y. T. Cheng, T. P. Vispute, R. Xiao and G. W. Huber, *Energy Environ. Sci.*, 2011, **4**, 2297–2307.
- 59 T. P. Vispute, H. Y. Zhang, A. Sanna, R. Xiao and G. W. Huber, *Science*, 2010, **330**, 1222–1227.
- 60 U. Mentzel, A. Rovik and C. Christensen, *Catal. Lett.*, 2009, **127**, 44–48.
- 61 A. Demirbas, *Energy Sources, Part A*, 2009, **31**, 1056–1062.
- 62 M. Kaarsholm, B. Rafii, F. Joensen, R. Cenni, J. Chaouki and G. S. Patience, *Ind. Eng. Chem. Res.*, 2010, **49**, 29–38.
- 63 J. M. Cho, J. M. Davis and G. W. Huber, *ChemSusChem*, 2010, **3**, 1162–1165.
- 64 Y. C. Lin, J. Cho, G. A. Tompsett, P. R. Westmoreland and G. W. Huber, *J. Phys. Chem. C*, 2009, **113**, 20097–20107.
- 65 P. J. Dauenhauer, J. L. Colby, C. M. Balonek, W. J. Suszynski and L. D. Schmidt, *Green Chem.*, 2009, **11**, 1555–1561.
- 66 P. R. Patwardhan, J. A. Satrio, R. C. Brown and B. H. Shanks, *J. Anal. Appl. Pyrolysis*, 2009, **86**, 323–330.
- 67 T. R. Carlson, J. Jae, Y. C. Lin, G. A. Tompsett and G. W. Huber, *J. Catal.*, 2010, **270**, 110–124.
- 68 I. M. Dahl and S. Kolboe, *J. Catal.*, 1994, **149**, 458–464.
- 69 I. M. Dahl and S. Kolboe, *J. Catal.*, 1996, **161**, 304–309.
- 70 M. Stocker, *Microporous Mesoporous Mater.*, 1999, **29**, 3–48.
- 71 J. F. Haw, W. G. Song, D. M. Marcus and J. B. Nicholas, *Acc. Chem. Res.*, 2003, **36**, 317–326.

-
- 72 D. M. McCann, D. Lesthaeghe, P. W. Kletnieks, D. R. Guenther, M. J. Hayman, V. Van Speybroeck, M. Waroquier and J. F. Haw, *Angew. Chem., Int. Ed.*, 2008, **47**, 5179–5182.
- 73 M. Bjorgen, S. Svelle, F. Joensen, J. Nerlov, S. Kolboe, F. Bonino, L. Palumbo, S. Bordiga and U. Olsbye, *J. Catal.*, 2007, **249**, 195–207.
- 74 M. Bjorgen, S. Akyalcin, U. Olsbye, S. Benard, S. Kolboe and S. Svelle, *J. Catal.*, 2010, **275**, 170–180.
- 75 C. M. Wang, Y. D. Wang, H. X. Lie, Z. K. Xie and Z. P. Liu, *J. Catal.*, 2010, **271**, 386–391.
- 76 A. G. Gayubo, B. Valle, A. T. Aguayo, M. Olazar and J. Bilbao, *Energy Fuels*, 2009, **23**, 4129–4136.
- 77 R. J. Evans and T. Milne, *ACS Symp. Ser.*, 1988, **376**, 311–327.
- 78 T. R. Carlson, J. Jae and G. W. Huber, *ChemCatChem*, 2009, **1**, 107–110.
- 79 From <http://www.icis.com/v2/magazine/home.aspx/>.